

Styrolux 684D

Styrene Butadiene Copolymer (SBC)

TECHNICAL
DATASHEET

DESCRIPTION

Styrolux® 684D is a clear styrene-butadiene copolymer (SBC) used in injection molding for parts with enhanced toughness as well as in sheet and film extrusion and blow molding. Parts made of Styrolux® 684D reveal excellent printability.

FEATURES

- High clarity
- Improved toughness
- Good printability

APPLICATIONS

- Food and non-food packaging
- Container, cups and lids
- Toys
- Extruded sheet and thin film
- Medical devices
- Blow moldings

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm ³ /10 min	11
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	4
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m ²	3
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	4
Tensile Stress at Yield, 23 °C	ISO 527	MPa	26
Tensile Strain at Yield, 23 °C	ISO 527	%	2.3
Nominal Strain at Break, 23 °C	ISO 527	%	160
Tensile Modulus	ISO 527	MPa	1500
Tensile Creep Modulus (1000h)	ISO 899	MPa	790
Tensile Creep Modulus (1h)	ISO 899	MPa	1300
Flexural Strength, 23 °C	ISO 178	MPa	40
Flexural Modulus, 23 °C	ISO 178	MPa	1700
Hardness, Shore D	ISO 868	-	68
Thermal Properties			

Styrolux 684D

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	59
Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h)	ISO 306	°C	83
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	59
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	73
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	60 - 90
Electrical Properties			
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.575
Light Transmission at 550 nm	ASTM D 1003	%	89
Haze	ASTM D 1003	%	< 1.5
Other Properties			
Density	ISO 1183	kg/m ³	1010
Water Absorption, Saturated at 23 °C	ISO 62	%	0.07
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 1

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities.

Please consult our local sales or technical representatives for details.

SUPPLY FORM

Styrolux is supplied in pellet form and should be kept in its original containers in cool, dry place. Avoid direct exposure to sunlight. Styrolux® can be stored in silos at temperatures well below 45 °C.

PRODUCT SAFETY

During processing of Styrolux® small quantities of styrene monomer may be released into the atmosphere. At styrene vapor concentrations below 20 ppm no negative effects on health are expected. In our experience, the concentration of styrene does not exceed 1 ppm in well ventilated workplaces - that is where five to eight air changes per hour are made. For safety information please refer to our Material Safety Data Sheet for this product.

DISCLAIMER

Styrolux 684D

Styrene Butadiene Copolymer (SBC)

TECHNICAL
DATASHEET

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.
